











CARATTERISTICHE TECNICHE - TECHNICAL FEATURES

	standards	characteristics or properties	declared values
	ISO 10545-3	assorbimento d'acqua water absorption	<0.5%
	ISO 10545-4	resistenza alla flessione (R) breaking strength	35 N/mm ²
	ISO 10545-13	resistenza agli acidi resistance to acid	GLA
	ISO 10545-12	resistenza al gelo frost resistance	resiste frost proof
	ISO 10545-14	resistenza alle macchie stain resistance	4
	ISO 10545-2	planarità surface flatness	±0.5%
	ISO 10545-2	durezza di Mohs hardness in Mohs degrees	6
		spessore thickness	10 mm
	DIN 51097 DIN 51130 DCOF BOT3000	coefficiente d'attrito (scivolosità) static coefficient of friction	A R9 >0.42
		variazioni cromatiche color shade	V2 variazione leggera V2 slight variation

IMBALLI - PACKING

mm	inch		spessore thickness	pezzi/sc pcs/box	m ² /sc sqm/box	kg/sc kgs/box	sc/pl box/pal	m ² /pl sqm/pal	kg/pl kgs/pal
80x180	32"x72"	rettificato polished satin	10	2	2.88	64.45	20.00	57.60	1289.00
60x120	24"x48"	rettificato polished satin	10	2	1.44	32.03	30.00	43.20	960.90
60x60	24"x24"	rettificato polished satin	10	3	1.08	24.65	40.00	43.20	986.00
30x60	12"x24"	rettificato polished satin	10	6	1.08	24.53	40.00	43.20	981.20
7.4x30	3"x12"	rettificato polished satin	10	40	0.89	20.44	60.00	53.28	1226.40
30X30	12"x12"	mosaico polished satin		11	0.99	19.70	36.00	35.64	709.20
7x60	3"x24"	battiscopa polished satin		12		12.60			

il peso riportato è comprensivo del pallet di supporto - the indicated weight includes the supporting pallet - le poids indiquè est compris de la palette de support - das angegebene gewicht versteht sich einschließlich der palette

FUGHE - JOINT - JOINT - FUGE

per materiale rettificato prevedere una fuga di almeno 2 mm sul monoformato e necessariamente 3 mm sul multiformato
 for rectified material, we recommend a 2 mm grout at least when using one size only and a 3 mm grout for multisizes laying solution
 pour le matériel rectifié prévoir un minimum de 2mm de joint et 3mm pour la pose multiformat

fuer retifiziertes material-monoverlegung wollen sie bitte eine fuge von 2 mm vorsehen – fuer moduverlegung eine fuge von 3 mm